

DUTRAL[®] K EP(D)M

CO 054

Ethylene - Propylene Copolymer

Dutral[®] K CO 054 is an Ethylene - Propylene polymer produced by suspension polymerisation using a Ziegler-Natta Catalyst at the Yeosu production facility in Korea.
A non-staining antioxidant is added during the production process.

Main Properties	Unit	Typical Value
Mooney Viscosity ML 1+4(100 °C)	MU	44
Volatiles content	% wt	0.5 max
Ash content	% wt	0.3 max
Propylene content	% wt	41
Ethylene content	% wt	59

Key Features

Dutral[®] K elastomers are characterized by excellent resistance to ageing and weathering, good resistance to both high and low temperatures, low permanent set values, good resistance to a large number of chemicals.

Dutral[®] K CO 054 is an amorphous copolymer of medium molecular weight and medium-broad molecular weight distribution.

It has good low temperature performance and processability, also on an open mill.

Main Applications

Automotive, cables, mechanical goods, building, bitumen modification, polymer modification, appliances.

Physical Form

Bales wrapped with natural polyethylene film.

Packaging

Disposable metal crate, nominal net weight 900 kg;
25 Kg bale, 36 bales per crate (1470 x 1140 x H1130 mm).

Storage Conditions

Store in vented, dry area at temperatures between 20°C and 30°C; no direct sunlight.

Shelf life : 36 months.

LOTTE VERSALIS ELASTOMERS CO. LTD

® Registered Trademark

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor liability accepted with respect to the use of such information and data.