

INTENE[®] K BR

40 AF
Butadiene Rubber

Intene[®] K 40 AF is a solution polymerized low cis polybutadiene produced using an alkyl lithium catalyst at the Yeosu production facility in Korea.

A TNPP/BHT free, food contact approved, non-staining antioxidant is added during the production process.

Main Properties	Test Method	Unit	Typical Value
Solution Viscosity	Internal Method	cP	100 ⁽¹⁾
Cis - 1:4 Content	Internal Method	%	38
Gel Rating	Internal Method		5 max
Colour	Internal Method		5
Volatile Matter	ASTM D 5668	% wt	0.75 max

⁽¹⁾5% wt/wt in Styrene at 25°C

Key Features

Low cis BR is the polybutadiene of choice to produce high impact Polystyrene (HIPS). It is particularly suited to HIPS processes where a lower solution viscosity is required.

Main Applications

Impact improver to be used in polystyrene and ABS manufacturing.

Physical Form

Water white to pale amber coloured bales wrapped in styrene soluble film.

Packaging

Returnable metal crate, nominal net weight 1188 kg;
33 Kg bale, 36 bales per crate (1465 x 150 x H1123 mm).

Storage Conditions

Store in a vented, dry area at temperatures between 20°C and 30°C; no direct sunlight.
Shelf life: 12 months minimum.

LOTTE VERSALIS ELASTOMERS CO. LTD

® Registered Trademark

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor liability accepted with respect to the use of such information and data.