

INTENE[®] K BR

50
Butadiene Rubber

Intene[®] K 50 is a solution polymerized low cis poly butadiene produced using an alkyl lithium catalyst at the Yeosu production facility in Korea. A non-staining antioxidant is added during the production process.

Main Properties	Test Method	Unit	Typical Value
Mooney Viscosity ML 1+4(100 °C) unmassed	ASTM D 1646	MU	48
Cis - 1:4 Content	Internal Method	%	38
Volatile Matter	ASTM D 5668	% wt	0.75 max

Key Features

Intene[®] K 50 is an elastomer characterised by an excellent resistance to abrasion, high resilience/rebound, good resistance to fatigue cracking and crack growth.
Its low glass transition temperature provides good low temperature performance.
Intene[®] K 50 reduces reversion in NR compounds, allowing higher temperature to be adopted.
It exhibits low BIT times and can also accept higher loadings of carbon black.

Main Applications

Tyres, belting, moulded and extruded articles.

Physical Form

Water-white to pale amber coloured bales wrapped in easy dispersible polyethylene film.

Packaging

Returnable metal crate, nominal net weight 1188 kg;
33 Kg bale, 36 bales per crate (1465 x 1150 x H1123 mm).

Storage Conditions

Store in a vented, dry area at temperatures between 20°C and 30°C; no direct sunlight.
Shelf life: 12 months minimum.

LOTTE VERSALIS ELASTOMERS CO. LTD

® Registered Trademark

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor liability accepted with respect to the use of such information and data.