

EUROPRENE® K S-SBR

SOL R 72613 Styrene-Butadiene Copolymer

Europrene® K SOL R 72613 is a solution polymerized, dry styrene-butadiene random copolymer and contains a non-staining antioxidant. It is produced by batch polymerization process at the Yeosu production facility in Korea.

Main Properties	Test Method	Unit	Typical Value
Mooney Viscosity ML 1+4(100 °C)	ASTM D 1646	MU	65
Bound Styrene	ASTM D 5775	% wt	21
Vinyl content	Internal Method	% wt	65 ⁽¹⁾
Volatile Matter	ASTM D 5668	% wt	0.75 max
Ash	ASTM D 5667	% wt	0.2 max
Tg	Internal Method	°C	-22

⁽¹⁾ Referred to butadiene portion

Key Features

Europrene® K SOL R 72613 is specifically designed to show a good trade-off between processability and final properties.

Main Applications

Silica - based compounds for high performance tyre treads high quality technical rubber goods. Thanks to its clear colour, Europrene® K SOL R 72613 is suitable for coloured articles

Physical Form

Clear bales wrapped in easily dispersible polyethylene film.

Packaging

Returnable metal crate, nominal net weight 990 kg;
33 kg bale, 30 bales per crate (1465 x 1150 x H1123 mm).

Storage Conditions

Store in a vented, dry area at temperatures between 20°C and 30°C; no direct sunlight.
Shelf life: 12 months minimum.

LOTTE VERSALIS ELASTOMERS CO. LTD

® Registered Trademark

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor liability accepted with respect to the use of such information and data.